Technical Data Sheet

3D-basics

Version/Printdate: 28.11.2023

Value Resin

Product specifications

BASIC RESIN is a liquid monomer for use with DLP and LCD 3D Printer. Mechanical properties like PLA and thermal properties like ABS, which combines easy printability, high thermal stability and stiffness.

Printing parameters Specimens printed on an Anycubic Photon 1 at 23°C and 50% hu-

midity 0,05mm layerheight 10 seconds exposuretime per layer

Postcuring parameters 30min with 200W 405nm UV LED Conditioned 72h at 23°C and

50% humidity

Physical properties after post curing

This data provided for those properties are typical values, and should not be construed as sales specifications.

Property	Method	Value	Unit
Young's modulus (Bending)	ISO 527	3100	MPa
Young's modulus (Pull)	ISO 527	6400	MPa
Elongation at break	ISO 527	5	%
Tensile Strenght	ISO 527	50 MPa	MPa
Charpy impact test		17 k	J/m²
HDT B		65,3	°C
Density ρ		1,21	g/cm3

Hazard Information

For detailed Hazard Information please refer to the Safety Data Sheet on 3d-basics.com/downloads

Storage Handling

Provided proper storage and handling precautions are taken we would expect Basic Reisin to be technically stable for at least 12 months. For detailed advice on Storage and Handling please refer to the Safety Data Sheet on 3d-basics.com/downloads.

Disclaimer

All other information supplied, including that herein, is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine a product's suitability for a particular purpose. We make no warranty, express or implied, including regarding any information supplied or the data upon which it is based or the results to be obtained from the use of such products or information, or concerning product, whether of satisfactory quality, merchantability, fitness for any particular purpose or otherwise, or with respect to intellectual property infringement as a result of use of information or products, and none shall be implied.